

Productinformation VARIABLES

ASMAPRENE BE

Property	Test specification	Units	Asmaprene BE				
			40	50	60	70	80
Hardness Shore A/D	ISO 868	Shore A Shore D					
Tensile strength	ISO 37	N/mm ²	10	17	21	27	29
Elongation at break	ISO 37	%	1280	1160	1050	950	830
Tear propagation resistance (Graves)	ISO 34	N/mm ²	12	15	18	32	31
Abrasion resistance		%	48	53	53	52	48
Rebound resilience	ISO 4662	%			55	47	
Compression set 70h/23°C 24h/70°C	ISO 815	%	19 12	20 7			37 18
Specific Gravity		g/cm ³	1,17	1,18	1,19	1,20	1,20

Please contact us for further information.